

TS1-CI

Surface Tolerant Epoxy Coating With Corrosion Inhibitor



DATA SHEET

Epoxy coating, 100% solids, with NANOTECHNOLOGY for iron oxide encapsulation and corrosion inhibitor, allowing metallic substrates with existing corrosion to be coated using only mechanical cleaning (St2). Excellent chemical resistance in the presence of caustics and acids. Easily applied with brush, roller, or airless spray.

- Can be applied up to 350 microns without sagging
- Extreme adhesion on steel, bronze, aluminum, concrete
- Protection against corrosion and chemical attack

APPLICATION AREAS

- Pipes
- Valves
- Water Boxes
- Centrifugal pumps
- Metal structures
- Reactors
- Tanks
- Heat exchangers
- Fans
- Flotation cells
- Impellers

COVERAGE

2 GL kit covers 21.4 m² (230 sf)
0.35 mm thickness (14 mils)

COLOR

Gray or white

PACKAGING

| Size | Coverage | Gray | White |
|------|--------------------|------------|------------|
| 2 GL | 21.4m ² | TS1CI-G2GL | TS1CI-W2GL |

TECHNICAL DATA

| | | | |
|--|------------------------------|-----------------|----------------|
| Maximum Temperature (depending on the service) | Wet Service Dry Service | 120°C 200°C | 248°F 392°F |
| Solids by Volume | 100% | | |
| Mixed Density | 1.25 | | |
| Shore D Hardness | (ASTM D 2240) | 84 | |
| Pot Life | 40 min / kg at 72°F | | |
| SAG Vertical Resistance at 21°C (70°F) and 0.350mm (14mils) | No sagging | | |
| Mixing Ratio | 2:1 by Weight | Base: Activator | |
| Shelf Life (unopened containers) | 3 years at 55-95°F (13-35°C) | | |



Taurus Epoxy, Inc.
4450 NW 126th Ave, Suite 107
Coral Springs, FL 33065 USA
Tel: (561) 757 - 5620
E-mail: taurus@taurusepoxy.com
Website: www.taurusepoxy.com



TAURUS EPOXY
COATINGS

TS1-CI

Surface Tolerant Epoxy Coating With Corrosion Inhibitor

SURFACE PREPARATION

Proper surface preparation is essential for the long-term performance of this product. The exact surface preparation requirements vary depending on the severity of the application, the expected service life, and the initial condition of the substrate. All sharp edges and welds must be ground to a 3 mm (120 mil) radius using an abrasive disc. Taurus TS1-CI is a "Surface Tolerant" coating with nanotechnology that allows for minimal preparation using mechanical cleaning (St2). This is typically achieved through initial cleaning and degreasing followed by mechanical preparation or water jetting.

MIX

Mix the activator well in the base with the mixing rod scraping the sides and the bottom of the container. Mix by weight 2 parts Base to 1 part of Activator. Mix thoroughly to produce a uniform and without stripes. Never put solvents.

APPLICATION TEMPERATURE

Keep between 55 and 95°F (17 to 35°C). Substrate: Keep between 45 and 105°F (7 to 40°C). The temperature difference of the substrate and material should never exceed 10°F (5°C). The substrate shall be at least 5°F (3°C) above the dew point. Do not apply if the relative humidity exceeds 90%. If necessary, heat the metal before surface preparation using electric heater or heat lamp. Never use gas, oil or kerosene heaters, as they will leave a greasy residue on the metal surface. For best results, keep all material in the warm zone overnight (75°F+) for easy mixing.

CURED TIME


| | 16°C (60°F) | 25°C (77°F) | 32°C (90°F) |
|-------------------|-------------|-------------|-------------|
| Tack Free | 4 hours | 2 hours | 1 hour |
| Light Load | 6 hours | 4 hours | 3 hours |
| Term Overlay | 10 hours | 8 hours | 4 hours |
| Full Charge | 14 hours | 16 hours | 8 hours |
| Complete Chemical | 36 hours | 24 hours | 18 hours |

FDA COMPLIANCE

This product complies with FDA regulations: FDA 21 CFR 175.300 and FDA 21 CFR 175.105.

APPLICATION

Brush: Medium to stiff bristles of sufficient quality to prevent shedding or bristles sticking to the coating (epoxy-set bristle brushes are preferred).
Cutting in or masking: Use tape with <1" nap.
Roller: Use good quality 1/8" nap.



CLEAN

Tools should be thoroughly cleaned immediately after use with a strong alkaline detergent.

SAFETY

Before using any product, review the Safety Data Sheet (SDS) or Safety Data Sheet for your area. Follow standard confined space entry and work procedures, if applicable.

Manufacturer, Taurus Epoxy Inc., makes no warranty either expressed or implied including warranties of merchantability or fitness for a particular purpose for this product. Under no circumstances will the manufacturer be liable for incidental, consequential, or other damages, breach of warranty, strict liability, or any other theory arising out of use of this product. The information and or recommendations contained herein are based on standard Product and are proprietary and furnished solely for the use of our customers. This information is provided in good faith and believed to be true and accurate as of the date/version of this document. As the manufacturer has no control over the use conditions or application process of the parties using this product, the manufacturer cannot accept responsibility for loss, injury or other damages resulting from the use of the Product or this or any other information provided by the manufacturer. Therefore, no guarantees of any kind, expressed or implied, are made by the manufacturer, Taurus Epoxy Inc., regarding this, or any, product manufactured by them or any contracted or licensed manufacturer. Taurus epoxy products do not provide structural integrity or improvement. They are only used to provide protection from corrosion, wear, abrasion and chemical attack on a given substrate and only to the extent provided for in the Data Sheets, Technical Data Sheets, Safety Data Sheets, and any other information as supplied in writing directly from manufacturers technical support.



Taurus Epoxy, Inc.
4450 NW 126th Ave, Suite 107
Coral Springs, FL 33065 USA
Tel: (561) 757 - 5620
E-mail: taurus@taurusepoxy.com
Website: www.taurusepoxy.com

