

# TX5-HT

## High Temperature Rapid Curing Ceramic Epoxy Compound



### DATA SHEET

Fast-curing, 100% solids Novolac epoxy compound, ceramic-filled and reinforced with aramid fiber matrix, offering resistance to abrasion and impact. Good chemical resistance in the presence of caustics and acids. Suitable for temperatures up to 280°C. Easily applied with a trowel, spatula, or by hand using latex gloves.

- Perfect for quick repairs and patching
- Extreme adhesion on steel, bronze, aluminum, concrete
- Protection for corrosion and abrasion

### APPLICATION AREAS

- Chutes
- Hoppers
- Carbon crushers
- Cyclones
- Centrifugal pumps
- Impellers
- Ash separators
- Screw conveyors
- Slurry distributors
- Wear plates
- Pipe elbows

### COVERAGE

10kg kit covers 0.8 m<sup>2</sup> (8.6 sf)  
Thickness: 6 mm (240 mils)

### COLOR

Red and blue

### PACKAGING

Size	Reorder #	Size	Reorder #	Size	Reorder #	Size	Reorder #
1 kg	TX5HT-01	2 kg	TX5HT-02	10 kg	TX5HT-10	20 kg	TX5HT-20

### TECHNICAL DATA

Maximum Temperature (depending on the service)	Wet Service Dry Service	230°C 280°C	446°F 536°F
Solids by Volume	100%		
Viscosity	Paste		
Mixed Density	2.0		
Shore D Hardness	(ASTM D 2240)	84	
Pot Life	25 min / kg at 72°F		
SAG Vertical Resistance at 21°C (70°F) and 6mm (240mils)	No sagging		
Mixing Ratio	2:1 by Weight	Base: Activator	
Shelf Life (unopened containers)	3 years at 55-95°F (13-35°C)		



Taurus Epoxy, Inc.  
4450 NW 126th Ave, Suite 107  
Coral Springs, FL 33065 USA  
Tel: (561) 757-5620  
E-mail: [taurus@taurusepoxy.com](mailto:taurus@taurusepoxy.com)  
Website: [www.taurusepoxy.com](http://www.taurusepoxy.com)



# TX5-HT

## High Temperature Rapid Curing Ceramic Epoxy Compound

### SURFACE PREPARATION

Proper surface preparation is essential for the long-term performance of this product. The exact surface preparation requirements vary depending on the severity of the application, expected service life, and the initial condition of the substrate. All sharp edges and welds must be ground to a 3 mm (120 mil) radius using an abrasive disc. Optimal preparation will result in a thoroughly clean surface, free of all contaminants, and roughened to an angular profile between 75–125 µm (3–5 mils). This is typically achieved through initial cleaning and degreasing, followed by abrasive blasting to a near-white metal finish, or by mechanical preparation.

### MIX

Thoroughly mix the activator into the base using a mixing stick, scraping the sides and bottom of the container. Mix at a ratio of 2 parts Base to 1 part Activator by weight. Blend thoroughly until a uniform, streak-free material is achieved. Never add solvents.

### APPLICATION

Use heavy plastic squeegee or putty knife to apply a 3mm minimum thickness. Work material into profile of substrate to achieve maximum adhesive and to remove any entrapped air. Contour to correct form with putty knife or plastic applicator. If mold or form is used be sure to coat its surface with a release agent to prevent adhesion of the material.

### APPLICATION TEMPERATURE

Maintain between 55 and 95°F (17 to 35°C).  
Substrate: Maintain between 45 and 105°F (7 to 40°C).  
The temperature difference between the substrate and the material should never exceed 10°F (5°C). The substrate must be at least 5°F (3°C) above the dew point. Do not apply if relative humidity exceeds 90%. If necessary, preheat the metal before surface preparation using an electric heater or heat lamp. Never use gas, oil, or kerosene heaters, as they will leave an oily residue on the metal surface. For best results, keep all material in a warm area overnight (75°F or higher) to ease mixing.



### CURED TIME

	16°C (60°F)	25°C (77°F)	32°C (90°F)
Tack Free	45 min	30 min	20 min
Light Load	1 hour	45 min	30 min
Overcoat End	1 hour	45 min	30 min
Full Charge	1.5 hours	1 hour	45 min

### CLEAN

Tools should be thoroughly cleaned immediately after use with a strong alkaline detergent.

### SAFETY

Before using any products, review the appropriate Safety Data Sheet (SDS) or Safety Sheet for your area. Follow standard confined space entry and work procedures, if appropriate.

Manufacturer, Taurus Epoxy Inc., makes no warranty either expressed or implied including warranties of merchantability or fitness for a particular purpose for this product. Under no circumstances will the manufacturer be liable for incidental, consequential, or other damages, breach of warranty, strict liability, or any other theory arising out of use of this product. The information and or recommendations contained herein are based on standard Product and are proprietary and furnished solely for the use of our customers. This information is provided in good faith and believed to be true and accurate as of the date/version of this document. As the manufacturer has no control over the use conditions or application process of the parties using this product, the manufacturer cannot accept responsibility for loss, injury or other damages resulting from the use of the Product or this or any other information provided by the manufacturer. Therefore, no guarantees of any kind, expressed or implied, are made by the manufacturer, Taurus Epoxy Inc., regarding this, or any, product manufactured by them or any contracted or licensed manufacturer. Taurus epoxy products do not provide structural integrity or improvement. They are only used to provide protection from corrosion, wear, abrasion and chemical attack on a given substrate and only to the extent provided for in the Data Sheets, Technical Data Sheets, Safety Data Sheets, and any other information as supplied in writing directly from manufacturers technical support.



Taurus Epoxy, Inc.  
4450 NW 126th Ave, Suite 107  
Coral Springs, FL 33065 USA  
Tel: (561) 757 – 5620  
E-mail: [taurus@taurusepoxy.com](mailto:taurus@taurusepoxy.com)  
Website: [www.taurusepoxy.com](http://www.taurusepoxy.com)

