

T150

Pipe Reinforcement Resin up to 150°C (320°F)



DATA SHEET

Taurus T150 is a 100% solids, solvent-free epoxy resin formulated for structural reinforcement applications using composite materials. It is designed for use with carbon fiber and fiberglass systems, providing high reliability and excellent performance under a wide range of service conditions. It is suitable for applications exposed to temperatures up to 150°C (302°F).

- Can be applied by brush or roller
- Compatible with steel, bronze, aluminum, and concrete
- Corrosion protection and structural reinforcement

APPLICATION AREAS

- Metal structures
- Pipe connections
- Pipelines
- Tank walls
- Vessels
- Many other

COLOR

Transparent amber

PACKAGING

Size	Reorder #	Size	Reorder #
1 kg	T150-01	50 kg	T150-50

TECHNICAL DATA

Maximum Temperature (depending on the service)	Wet Service Dry Service	90°C 150°C	194°F 320°F
Solids by Volume	100%		
Mixed Density	1.25		
Shore D Hardness	(ASTM D 2240)	85	
Pot Life	25 min / kg at 72°F		
Mixing Ratio	2.6:1 by Weight	Base: Activator	
Shelf Life (unopened containers)	3 years at 55-95°F (13-35°C)		



Taurus Epoxy, Inc.
4450 NW 126th Ave, Suite 107
Coral Springs, FL 33065 USA
Tel: (561) 757 - 5620
E-mail: taurus@taurusepoxy.com
Website: www.taurusepoxy.com



SURFACE PREPARATION

Proper surface preparation is critical to the long-term performance of this product. The exact requirements for surface preparation vary with the severity of the application, the expected useful life and the initial conditions of the substrate. All sharp edges and welds shall be roughed to a radius of 3mm (120 thousand) with abrasive disc. The optimal preparation will provide a thoroughly cleaned surface of all contaminants and rough to an angular profile between 75-125 µm (3-5 mil). This is normally achieved by initial cleaning and degreasing and then abrasive blasting to near-white metal cleaning, or by mechanical preparation.

MIX

Mix the activator well in the base with the mixing rod scraping the sides and the bottom of the container. Mix by weight 2.6 parts Base to 1 part of Activator. Mix thoroughly to produce a uniform and without stripes. Never put solvents.

APPLICATION TEMPERATURE

Keep between 55 and 95°F (17 to 35°C). Substrate: keep between 45 and 105°F (7 to 40°C). The temperature difference of the substrate and material should never exceed 10°F (5°C). The substrate shall be at least 5°F (3°C) above the dew point. Do not apply if the relative humidity exceeds 90%. If necessary, heat the metal before surface preparation using electric heater or heat lamp. Never use gas, oil or kerosene heaters, as they will leave a greasy residue on the metal surface. For best results, keep all material in the warm zone overnight (75°F+) for easy mixing.

CURED TIME

	16°C (60°F)	25°C (77°F)	32°C (90°F)
Tack Free	4 hours	2 hours	1 hour
Light Load	12 hours	6 hours	3 hours
Term Overlay	16 hours	10 hours	5 hours
Full Charge	24 hours	12 hours	6 hours
Complete Chemical	48 hours	24 hours	12 hours

APPLICATION

Use a heavy plastic brush or putty knife to apply a minimum thickness of 6 mm. Work the material in the substrate profile to achieve maximum adhesive and remove any trapped air. Contour to correct the shape with putty knife material or plastic applicator. If mold is used or shape, be sure to coat its surface with an agent of release to prevent adhesion of the material.



CLEAN

Tools should be thoroughly cleaned immediately after use with a strong alkaline detergent.

SAFETY

Before using any product, review the Safety Data Sheet (SDS) or Safety Data Sheet for your area. Follow standard confined space work and entry procedures, if applicable.

Manufacturer, Taurus Epoxy Inc., makes no warranty either expressed or implied including warranties of merchantability or fitness for a particular purpose for this product. Under no circumstances will the manufacturer be liable for incidental, consequential, or other damages, breach of warranty, strict liability, or any other theory arising out of use of this product. The information and or recommendations contained herein are based on standard Product and are proprietary and furnished solely for the use of our customers. This information is provided in good faith and believed to be true and accurate as of the date/version of this document. As the manufacturer has no control over the use conditions or application process of the parties using this product, the manufacturer cannot accept responsibility for loss, injury or other damages resulting from the use of the Product or this or any other information provided by the manufacturer. Therefore, no guarantees of any kind, expressed or implied, are made by the manufacturer, Taurus Epoxy Inc., regarding this, or any, product manufactured by them or any contracted or licensed manufacturer. Taurus epoxy products do not provide structural integrity or improvement. They are only used to provide protection from corrosion, wear, abrasion and chemical attack on a given substrate and only to the extent provided for in the Data Sheets, Technical Data Sheets, Safety Data Sheets, and any other information as supplied in writing directly from manufacturers technical support.



Taurus Epoxy, Inc.
4450 NW 126th Ave, Suite 107
Coral Springs, FL 33065 USA
Tel: (561) 757 - 5620
E-mail: taurus@taurusepoxy.com
Website: www.taurusepoxy.com

