

TCS4

Industrial Flooring Epoxy Coating For Strong Chemicals



DATA SHEET

Broachable compound, 100% solid, Novolac epoxy with ceramic microsphere filling for protection of concrete floors with exposure to aggressive chemicals. Excellent chemical resistance with the presence of caustics and concentrated acids. It is easily applied with brush, roller and airless.

- Applies up to 1000 microns without sagging
- Suitable for immersion and non-immersion
- Protection against corrosion and abrasion

APPLICATION AREAS

- Collectors
- Concrete walls
- Foot of pumps
- Chemical tanks
- Concrete channels
- Ventilators
- Team bases
- Pits, tunnels
- Chemical floors
- Other

COVERAGE

7.5 kg kit covers 5.32 m² (57 sf)
1000 microns thickness (40 mils)

COLOR

Gray or blue. Green and red options

PACKAGING

Size	Reorder #	Size	Reorder #
7.5 kg	TCS4-7.5	15 kg	TCS4-15

TECHNICAL DATA

Maximum Temperature (depending on the service)	Wet Service Dry Service	65°C 85°C	149°F 185°F
Solids by Volume	100%		
Mixed Density	1.4		
Shore D Hardness	(ASTM D 2240)	84	
Pot Life	35 min / kg at 72°F		
SAG Vertical Resistance at 21°C (70°F) and 1mm (40mils)	No sagging		
Mixing Ratio	2:1 by Weight	Base: Activator	
Shelf Life (unopened containers)	3 years at 55-95°F (13-35°C)		



Taurus Epoxy, Inc.
4450 NW 126th Ave, Suite 107
Coral Springs, FL 33065 USA
Tel: (561) 757 – 5620
E-mail: taurus@taurusepoxy.com
Website: www.taurusepoxy.com



SURFACE PREPARATION

Proper surface preparation is vitally important for long-term performance. The prepared concrete surface must be structurally sound, free of all contaminants and rough to a profile >ICRI CSP 3 (similar to grain size #60 sandpaper). Taurus TCS4 can be applied directly on concrete or with the T497 primer to make vapor barrier. Cleaning can be done with water jet, scarifier, or abrasive jet.

MIX

Mix the activator well in the base with the mixing rod scraping the sides and the bottom of the container.
Mix by weight 2 parts Base to 1 part of Activator.
Mix thoroughly to produce a uniform and without stripes. Never put solvents.

APPLICATION

Brush: medium to rigid bristles of sufficient quality than bristles do not come loose and stick to the coating (brushes of epoxy glued bristles are better).
Trim or put tape <1" nap.
Roller: use a good quality 1/8" nap.

APPLICATION TEMPERATURE

Application temperature range from 10°C (50°F) to 32°C (90°F) (substrate).
For maximum protection against immersion or spillage, a 2-layer system is recommended.
To avoid sagging on vertical surfaces, the maximum thickness of the wet film should be between 500 µm - 1000 µm (20-40 mil) per layer.



CURED TIME

	16°C (60°F)	25°C (77°F)	32°C (90°F)
Tack Free	4 hours	2 hours	1 hour
Light Load	12 hours	6 hours	3 hours
Term Overlay	16 hours	10 hours	5 hours
Full Charge	24 hours	12 hours	6 hours
Complete Chemical	48 hours	24 hours	12 hours

CLEAN

Tools should be thoroughly cleaned immediately after use with a strong alkaline detergent.

SAFETY

Before using any product, review the Safety Data Sheet (SDS) or Safety Data Sheet for your area. Follow standard confined space work and entry procedures, if applicable.

Manufacturer, Taurus Epoxy Inc., makes no warranty either expressed or implied including warranties of merchantability or fitness for a particular purpose for this product. Under no circumstances will the manufacturer be liable for incidental, consequential, or other damages, breach of warranty, strict liability, or any other theory arising out of use of this product. The information and/or recommendations contained herein are based on standard Product and are proprietary and furnished solely for the use of our customers. This information is provided in good faith and believed to be true and accurate as of the date/version of this document. As the manufacturer has no control over the use conditions or application process of the parties using this product, the manufacturer cannot accept responsibility for loss, injury or other damages resulting from the use of the Product or this or any other information provided by the manufacturer. Therefore, no guarantees of any kind, expressed or implied, are made by the manufacturer, Taurus Epoxy Inc., regarding this, or any, product manufactured by them or any contracted or licensed manufacturer. Taurus epoxy products do not provide structural integrity or improvement. They are only used to provide protection from corrosion, wear, abrasion and chemical attack on a given substrate and only to the extent provided for in the Data Sheets, Technical Data Sheets, Safety Data Sheets, and any other information as supplied in writing directly from manufacturers technical support.

FDA COMPLIANCE

This product complies with FDA regulations: FDA 21 CFR 175.300 and FDA 21 CFR 175.105.



Taurus Epoxy, Inc.
4450 NW 126th Ave, Suite 107
Coral Springs, FL 33065 USA
Tel: (561) 757 - 5620
E-mail: taurus@taurusepoxy.com
Website: www.taurusepoxy.com

