

TFLEX-MEMBRANE

Concrete Flexible Epoxy Membrane



DATA SHEET

Flexible compound, 100% solids, epoxy filled with ceramic microspheres to seal tank bases with excellent adhesion to metals, concrete, and other substrates. TFLEX-Membrane is liquid and can be easily applied in thicknesses up to 1 mm without sagging on vertical surfaces. It provides excellent chemical resistance, great flexibility, and elongation.

- For tank bases, concrete slabs
- Provides excellent sealing between concrete and metal
- Easily applicable on horizontal and vertical surfaces

APPLICATION AREAS

- Concrete slabs
- Concrete walls
- Collectors
- Pump bases
- Tanks bases
- Secondary containment
- Concrete channels
- Equipment bases
- Pits, tunnels
- Floors
- Others

COVERAGE

10 kg kit covers 7m² (75 sf)
1 mm thickness (40 mils)

COLOR

Gray

PACKAGING

Size	Reorder #
10 kg	TFLEX-MEMBRANE10

TECHNICAL DATA

Maximum Temperature (depending on the service)	Wet Service Dry Service	-30°C 93°C	-22°F 200°F
Elongation	70%		
Mixed Density	1.4		
Pot Life	55 min / kg at 72°F		
Resistencia Vertical SAG at 21°C (70°F) and 1 mm (40mils)	No sagging		
Mixing Ratio	6:1 by Weight	Base: Activator	
Shelf Life (unopened containers)	3 years at 55-95°F (13-35°C)		



Taurus Epoxy, Inc.
4450 NW 126th Ave, Suite 107
Coral Springs, FL 33065 USA
Tel: (561) 757 – 5620
E-mail: taurus@taurusepoxy.com
Website: www.taurusepoxy.com



TFLEX-MEMBRANE

Concrete Flexible Epoxy Membrane

SURFACE PREPARATION

Proper surface preparation is of vital importance for long-term performance. The prepared concrete surface must be structurally sound, free of all contaminants, and roughened to a profile >ICRI CSP 3 (similar to #60 grit sandpaper). For metal, the minimum preparation should be mechanical cleaning St2/St3. Taurus TFLEX-Membrane can be applied directly onto metal and concrete.

MIX

Thoroughly mix the activator into the base using a mixing stick, scraping the sides and bottom of the container. Mix by weight at a ratio of 6 parts Base to 1 part Activator. Mix thoroughly until a uniform, streak-free material is obtained. Never add solvents.

APPLICATION TEMPERATURE

Application temperature range of 10°C (50°F) to 32°C (90°F) (substrate).

For maximum protection against immersion or spills, a 2-coat system is recommended.

To prevent sagging on vertical surfaces, the maximum wet film thickness should be between 500 µm – 1000 µm (20–40 mils) per coat.

APPLICATION

It can be applied by brush or roller.

To prevent sagging on vertical surfaces, the maximum wet film thickness should be up to 1 mm (40 mils) per coat.



CURED TIME

	16°C (60°F)	25°C (77°F)	32°C (90°F)
Tack Free	4 hours	2 hours	1 hour
Light Load	12 hours	6 hours	3 hours
Term Overlay	16 hours	10 hours	5 hours
Full Charge	24 hours	12 hours	6 hours
Complete Chemical	48 hours	24 hours	12 hours

CLEAN

Tools should be thoroughly cleaned immediately after use with a strong alkaline detergent.

SAFETY

Before using any product, review the Safety Data Sheet (SDS) or Safety Data Sheet for your area. Follow standard confined space work and entry procedures, if applicable.

Manufacturer, Taurus Epoxy Inc., makes no warranty either expressed or implied including warranties of merchantability or fitness for a particular purpose for this product. Under no circumstances will the manufacturer be liable for incidental, consequential, or other damages, breach of warranty, strict liability, or any other theory arising out of use of this product. The information and or recommendations contained herein are based on standard Product and are proprietary and furnished solely for the use of our customers. This information is provided in good faith and believed to be true and accurate as of the date/version of this document. As the manufacturer has no control over the use conditions or application process of the parties using this product, the manufacturer cannot accept responsibility for loss, injury or other damages resulting from the use of the Product or this or any other information provided by the manufacturer. Therefore, no guarantees of any kind, expressed or implied, are made by the manufacturer, Taurus Epoxy Inc., regarding this, or any, product manufactured by them or any contracted or licensed manufacturer. Taurus epoxy products do not provide structural integrity or improvement. They are only used to provide protection from corrosion, wear, abrasion and chemical attack on a given substrate and only to the extent provided for in the Data Sheets, Technical Data Sheets, Safety Data Sheets, and any other information as supplied in writing directly from manufacturers technical support.



Taurus Epoxy, Inc.
12481 NW 44th. Coral Springs FL 33065 USA
Tel: (561) 757 – 5620
E-mail: taurus@taurusepoxy.com
Website: www.taurusepoxy.com

